

Darwin Chemical Company
600 N Pine Island Road
Plantation FL 33324-1311



Tixogel MP-250

Tixogel MP-250

Catalog Nr.	Q138			
Definition	Maximum performance organoclay-Self-activating, easily dispersed thixotrope for printing ink.			
CAS Number				
Application	<p>Tixogel MP-250 is a new generation high performance, self-activating rheological additive for medium to high polarity solvent based ink systems.</p> <p>can be added to the pigment grind, requires no polar activator, and can often be utilized at lower loading levels than competitive self-activating organoclays</p>			
Technical Data	<p>PROPERTIES:</p> <p>Composition: Quaternary Ammonium Bentonite Complex Density: 13.85 lbs./U.S. gal. (1.66 g/cm³) Bulking Value: 0.072 U.S. gals./lb. Particle Size: Ultimate Dispersed Particle Size <1 µm Moisture Content: 2.5% maximum Color/Form: Light Buff Powder</p>			
Packaging & Handling	25 lbs bags			
	<table><thead><tr><th>UN Number</th><th>Class</th><th>Packaging Group</th></tr></thead></table>	UN Number	Class	Packaging Group
UN Number	Class	Packaging Group		
Remarks				

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for test results obtained by the application of this information or the safety and suitability of our products, either alone or in combination with other products. Users are advised to make their own test to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.